

You have 1 hour to finish the quiz. There are four problems and each is 25% of the total grade. For problem 3, pick one from A, B and C.

Use $T=300K$ unless specified otherwise. Make appropriate assumptions when necessary.

Constants for room temperature Si

$$n_i = 1.5 \cdot 10^{10} \text{ cm}^{-3}$$

$$E_g = 1.14 \text{ eV}$$

$$\epsilon_{Si} = 1.04 \cdot 10^{-12} \text{ F/cm}$$

$$q = 1.6 \cdot 10^{-19} \text{ C}$$

$$h = 6.63 \cdot 10^{-34} \text{ m}^2 \text{ kg/s} = 2\pi\hbar$$

$$k_B = 1.38 \cdot 10^{-23} \text{ m}^2 \text{ kg s}^{-2} \text{ K}^{-1} = 8.617 \cdot 10^{-5} \text{ eV K}^{-1}$$

$$p = \hbar k, E = \frac{\hbar^2 k^2}{2m}, m_{\text{eff}} = \hbar^2 / \left(\frac{\partial^2 E}{\partial k^2} \right)$$

$$f_F(E) = \frac{1}{1 + \exp\left(\frac{E - E_F}{kT}\right)}$$

$$n_0 p_0 = n_i^2 = N_c N_v \exp\left(-\frac{E_g}{kT}\right)$$

$$g_c(E) = \frac{4\pi(2m_n^*)^3}{h^3} \sqrt{E - E_c}, g_v(E) = \frac{4\pi(2m_p^*)^3}{h^3} \sqrt{E_v - E}$$

$$n_0 = N_c \exp\left[-\frac{(E_F - E_c)}{kT}\right] = n_i \exp\left[\frac{E_F - E_{Fi}}{kT}\right]$$

$$p_0 = N_v \exp\left[-\frac{E_v - E_F}{kT}\right] = n_i \exp\left[\frac{E_{Fi} - E_F}{kT}\right]$$

$$n_0 + N_a - p_a = p_0 + N_d - n_d$$

$$n_d = \frac{N_d}{1 + \frac{1}{2} \exp\left(\frac{E_d - E_F}{kT}\right)}, p_a = \frac{N_a}{1 + \frac{1}{4} \exp\left(\frac{E_F - E_a}{kT}\right)}$$

$$n_0 = \frac{N_d - N_a}{2} + \sqrt{\left(\frac{N_d - N_a}{2}\right)^2 + n_i^2}$$

$$|v| = \mu |E|, \quad \frac{1}{\mu} = \frac{1}{\mu_{\text{lattice}}} = \frac{1}{\mu_{\text{impurity}}}$$

$$J_{n,\text{drift}} = q\mu_n n E, J_{p,\text{drift}} = q\mu_p p E$$

$$J_{n,\text{diffusion}} = qD_n \frac{dn}{dx}, J_{p,\text{diffusion}} = -qD_p \frac{dp}{dx}$$

$$\sigma = q\mu_n n + q\mu_p p, \rho = 1/\sigma, \tau_d = \frac{\epsilon}{\rho}$$

$$\frac{D_n}{\mu_n} = \frac{D_p}{\mu_p} = \frac{kT}{q}$$

$$L_p^2 = D_p \tau_{p0}, L_n^2 = D_n \tau_{n0}$$

$$\frac{\partial p}{\partial t} = -\frac{1}{q} \frac{\partial J_p}{\partial x} + g_p - \frac{p}{\tau_{pt}}, \quad \frac{\partial n}{\partial t} = \frac{1}{q} \frac{\partial J_n}{\partial x} + g_n - \frac{n}{\tau_{nt}}$$

$$D_p \frac{\partial^2(\delta p_n)}{\partial x^2} - \mu_p E \frac{\partial(\delta p_n)}{\partial x} + g' - \frac{\delta p_n}{\tau_{p0}} = \frac{\partial(\delta p_n)}{\partial t}$$

$$D' = \frac{\mu_n n D_p + \mu_p p D_n}{\mu_n n + \mu_p p}, \quad \mu' = \frac{\mu_n \mu_p (p - n)}{\mu_n n + \mu_p p}$$

$$D_n \frac{\partial^2(\delta n_p)}{\partial x^2} - \mu_n E \frac{\partial(\delta n_p)}{\partial x} + g' - \frac{\delta n_p}{\tau_{n0}} = \frac{\partial(\delta n_p)}{\partial t}$$

$$\frac{\rho(x)}{\epsilon_s} = \frac{dE(x)}{dx} = \frac{-d^2\phi}{dx^2}$$

$$V_{bi} = \frac{kT}{q} \ln\left(\frac{N_a N_d}{n_i^2}\right), \quad V_B \approx \frac{\epsilon_s E_{\text{crit}}^2}{2qN_B}$$

$$x_n = \left\{ \frac{2\epsilon_s V_{bi}}{q} \left[\frac{N_a}{N_d} \right] \left[\frac{1}{N_a + N_d} \right] \right\}^{1/2}, \quad x_p = \left\{ \frac{2\epsilon_s V_{bi}}{q} \left[\frac{N_d}{N_a} \right] \left[\frac{1}{N_a + N_d} \right] \right\}^{1/2}$$

$$J_{\text{ideal}} = \left(\frac{qD_p p_{n0}}{L_p} + \frac{qD_n n_{p0}}{L_n} \right) \left(\exp\left(\frac{qV_a}{kT}\right) - 1 \right)$$

$$C' = \frac{dQ'}{dV_R} = \left\{ \frac{q\epsilon_s N_a N_d}{2(V_{bi} + V_R)(N_a + N_d)} \right\}^{1/2}$$

$$n_p = n_{p0} \exp\left(\frac{qV_a}{kT}\right), \quad p_n = p_{n0} \exp\left(\frac{qV_a}{kT}\right)$$

Some solutions for the ambipolar transport equation

$$\delta p(t) = \delta p(0) e^{-t/\tau_{p0}}$$

$$\delta p(t) = g' \tau_{p0} (1 - e^{-t/\tau_{p0}})$$


$$\delta p(x) = \delta p(0) e^{-|x|/L_p}$$

$$\delta p(x, t) = e^{-t/\tau_{p0}} * (4\pi D_p t)^{-\frac{1}{2}} * \exp\left[-\frac{(x - \mu_p E_0 t)^2}{4D_p t}\right]$$

Name:

UID:

1. (a) For intrinsic Si, use y-axis for energy and show the relative positions for the conduction band edge, valence band edge and the Fermi level. (b) In the figure from (a), sketch the Fermi-Dirac distribution, density of states functions for electrons and holes, carrier concentration for electrons and holes (total of 5 functions). (c) Now the Si is doped by a single dopant so that $E_F - E_{Fi} = 0.2\text{eV}$, What's the type of the dopant? What are the carrier concentrations now and what is the doping concentration? (d) Repeat (b) for the doped Si in (c).



2. (a) When we calculate the ideal current for a forward-biased diode (ignoring the recombination current), what are the four components of the current? In the figure, we showed one of the four components in the neutral p region. Which component is this one? (b) If $D_n = 25 \text{ cm}^2/\text{s}$, $D_p = 10 \text{ cm}^2/\text{s}$, $\tau_{n0} = 5 \cdot 10^{-7} \text{ s}$ and $\tau_{p0} = 5 \cdot 10^{-5} \text{ s}$ and the given current component is $10 \mu\text{A}$ at $-x_p$ and $N_a = N_d$, what is the total current of the forward-biased diode? Plot the total current in the same figure. (c) Sketch electron current and hole current in the neutral p region, depletion region and neutral n regions based on the information from (a) and (b).

Name:


UID:

3. Choose one from problem A, B, C

A: (a) Sketch how carrier mobility changes with temperature and explain. (b) For a moderately doped Si ($N_d \sim 10^{15} \text{ cm}^{-3}$), sketch its conductivity ($\log(\sigma)$) versus temperature ($1/T$).

B: Si is used as dopant (N_I) in GaAs. Suppose a fraction of the Si atoms, $\alpha\%$ replaces Ga and the other $1 - \alpha\%$ of Si atoms replaces As in the lattice. How will the Fermi level change in the GaAs with respect to α ?

C: (a) For a p-i-n junction with the linear dopant profile as shown in the figure, what's the applied reverse bias if the depletion width is $4 \mu\text{m}$? (b) Repeat (a) if the i-region is now replaced by metal ($\sigma = \infty$).



name:

UID:

4. Assume that a finite number of electron-hole pairs is generated instantaneously at $t = 0$ and $x = 0$ in an n-type semiconductor, assume the excess carrier generation rate is zero for $t > 0$.
- (a) Sketch excess carrier concentration with respect to x for $t = t_1, t = t_2, t = t_3$ (3 curves) and $t_3 > t_2 > t_1 > 0$ for no external field ($E_0 = 0$). (b) Repeat (a) for $E_0 > 0$. (c) Inspired by the result from (b), a very famous experiment is set up to measure the minority carrier mobility, minority carrier diffusion coefficient and minority excess carrier lifetime. What's the name of the experiment and what's its significance? Draw the set up for the experiment. (d) Describe how you can use it to measure the underlined parameters (you might need hint from the equation sheet).